

SPLOTY LIN STALOWYCH: SLS

Średnica	Waga 1 metra liny (kg)			Minimalna siła zrywająca przy znamionowej wytrzymałości drutów 1770 N/mm ² (kN)		
	Konstrukcja --->	1x7	1x19	1x37	1x7	1x19
fi. 1,0	0,00502	-	-	0,963	-	-
fi. 1,5	0,01130	0,0111	-	2,170	2,09	-
fi. 2,0	0,02010	0,0198	-	3,850	3,72	-
fi. 2,5	0,03140	0,0310	-	6,020	5,81	-
fi. 3,0	0,04520	0,0446	0,0440	8,670	8,37	8,160
fi. 3,5	0,06150	0,0607	-	11,80	11,4	-
fi. 4,0	0,08030	0,0793	0,0782	15,40	14,9	14,500
fi. 4,5	0,10200	-	-	19,50	-	-
fi. 5,0	0,12600	0,1240	0,1220	24,10	23,2	22,700
fi. 6,0	-	0,1780	0,1760	-	33,5	32,700
fi. 7,0	-	0,2430	0,2400	-	45,6	44,400

LINY Z RDZENIEM Z WŁÓKNA: LSO +A_o

Średnica	Waga 1 metra liny (kg)			Minimalna siła zrywająca przy znamionowej wytrzymałości drutów 1770 N/mm ² (kN)		
	Konstrukcja --->	6x7	6x19	6x37	6x7	6x19
fi. 1,8	0,0100	-	-	1,900	-	-
fi. 2,0	0,0143	-	-	2,350	-	-
fi. 2,5	0,0220	-	-	3,700	-	-
fi. 3,0	0,0322	0,0311	-	5,290	4,900	-
fi. 4,0	0,0572	0,0554	-	9,410	8,700	-
fi. 5,0	0,0894	0,0865	-	14,70	13,60	-
fi. 6,0	0,1290	0,1250	-	21,10	19,60	-
fi. 7,0	0,1750	0,1700	-	28,80	26,70	-
fi. 8,0	0,2290	0,2210	0,221	37,60	34,80	33,40
fi. 9,0	0,2890	0,2800	0,280	47,60	44,10	42,30
fi. 10,0	0,3570	0,3460	0,346	58,80	54,40	52,20
fi. 11,0	0,4320	0,4190	0,419	71,10	65,80	63,10
fi. 12,0	0,5150	0,4980	0,498	84,70	78,30	75,10
fi. 13,0	0,6040	0,5850	0,585	99,40	91,90	88,20
fi. 14,0	0,7010	0,6780	0,678	115,0	107,0	102,0
fi. 16,0	-	0,8860	0,886	-	139,0	134,0
fi. 18,0	-	1,1200	1,120	-	176,0	169,0
fi. 20,0	-	1,3800	1,380	-	218,0	209,0
fi. 22,0	-	1,6700	1,670	-	263,0	253,0
fi. 24,0	-	1,9900	1,990	-	313,0	301,0
fi. 26,0	-	-	2,340	-	-	353,0
fi. 28,0	-	-	2,710	-	-	409,0
fi. 32,0	-	-	3,540	-	-	534,0

LINY Z RDZENIEM STALOWYM: LSO +At

Średnica	Waga 1 metra liny (kg)			Minimalna siła zrywająca przy znamionowej wytrzymałości drutów 1770 N/mm ² (kN)			
	Konstrukcja --->	6x7	6x19	6x37	6x7	6x19	6x37
fi. 1,8		0,0130	-	-	2,060	-	-
fi. 2,0		0,0157	-	-	2,540	-	-
fi. 2,5		0,0245	-	-	3,970	-	-
fi. 3,0		0,0354	0,0342	-	5,710	5,290	-
fi. 4,0		0,0629	0,0609	-	10,20	9,400	-
fi. 5,0		0,0983	0,0952	-	15,90	14,70	-
fi. 6,0		0,1420	0,1380	-	22,90	21,20	-
fi. 7,0		0,1930	0,1870	-	31,10	28,80	-
fi. 8,0		0,2520	0,2430	0,244	40,60	37,60	36,10
fi. 9,0		0,3180	0,3080	0,308	51,40	47,60	45,70
fi. 10,0		0,3930	0,3810	0,381	63,50	58,80	56,40
fi. 11,0		0,4750	0,4610	0,461	76,80	71,10	68,20
fi. 12,0		0,5670	0,5480	0,548	91,50	84,60	81,20
fi. 13,0		0,6640	0,6430	0,643	107,0	99,30	95,20
fi. 14,0		0,7710	0,7460	0,746	124,0	115,0	110,0
fi. 16,0		-	0,9740	0,974	-	150,0	144,0
fi. 18,0		-	1,2300	1,230	-	190,0	183,0
fi. 20,0		-	1,5200	1,520	-	235,0	225,0
fi. 22,0		-	1,8400	1,840	-	284,0	273,0
fi. 24,0		-	2,1900	2,190	-	338,0	325,0
fi. 26,0		-	-	3,570	-	-	381,0
fi. 28,0		-	-	2,980	-	-	442,0
fi. 32,0		-	-	3,900	-	-	577,0

LINY STALOWE DŹWIGOWE: LSO WS

Średnica	Waga 1 metra liny (kg)				Minimalna siła zrywająca przy znamionowe wytrzymałości drutów 1770 N/mm ²			
	Rdzeń z włókna		Rdzeń stalowy		Rdzeń z włókna		Rdzeń stalowy	
Konstrukcja --->	6x36	6x31	6x36	6x31	6x36	6x31	6x36	6x31
fi. 8,0	0,250	0,231	0,270	0,255	37,4	37,4	40,4	40,3
fi. 9,0	0,310	0,292	0,340	0,322	47,3	47,3	51,1	51,0
fi. 10,0	0,390	0,361	0,420	0,398	58,4	58,4	63,1	63,0
fi. 11,0	0,470	0,437	0,510	0,482	70,6	70,7	76,3	76,2
fi. 12,0	0,547	0,520	0,602	0,573	84,0	84,1	89,9	90,7
fi. 13,0	0,643	0,610	0,707	0,673	98,3	98,7	106,0	106,5
fi. 14,0	0,745	0,708	0,820	0,780	114,0	114,5	124,0	123,5
fi. 16,0	0,973	0,924	1,070	1,019	149,0	149,5	161,0	161,3
fi. 18,0	1,230	1,170	1,350	1,290	189,0	189,2	204,0	204,2
fi. 20,0	1,520	1,444	1,670	1,592	234,0	233,6	252,0	252,0
fi. 22,0	1,840	1,747	2,020	1,926	282,0	282,7	304,0	305,0
fi. 24,0	2,190	2,079	2,410	2,292	336,0	336,4	363,0	362,9
fi. 26,0	2,570	-	2,830	-	395,0	-	425,0	-
fi. 28,0	2,980	-	3,280	-	458,0	-	493,0	-

LINY STALOWE SPECJALNE: LSO S

Średnica	Waga 1 metra liny (kg)				Minimalna siła zrywająca przy znamionowe wytrzymałości drutów 1770 N/mm ²			
	FILLER 6x19		SEAL 6x19		FILLER 6x19		SEAL 6x19	
Rdzeń --->	z włókna	stalowy	z włókna	stalowy	z włókna	stalowy	z włókna	stalowy
fi. 6,0	-	-	0,134	0,147	-	-	21,1	22,8
fi. 7,0	-	-	0,183	0,201	-	-	28,7	31,0
fi. 8,0	-	-	0,238	0,262	-	-	37,5	40,5
fi. 9,0	-	-	0,302	0,332	-	-	47,4	51,2
fi. 10,0	0,380	0,418	0,373	0,410	59,8	64,6	58,6	63,3
fi. 11,0	0,460	0,506	0,451	0,496	72,3	78,1	70,9	76,5
fi. 12,0	0,574	0,602	0,537	0,590	86,1	93,0	84,3	91,1
fi. 13,0	0,643	-	0,630	0,693	101,0	-	99,0	107,0
fi. 14,0	0,745	0,820	0,730	0,803	117,0	127,0	115,0	124,0
fi. 15,0	0,855	0,941	0,838	0,922	135,0	145,0	132,0	142,0
fi. 16,0	0,973	1,070	0,954	1,050	153,0	165,0	160,0	162,0
fi. 17,0	1,100	1,210	1,080	1,190	173,0	187,0	169,0	183,0
fi. 18,0	1,230	1,350	1,210	1,330	194,0	209,0	190,0	205,0
fi. 19,0	1,370	1,510	1,350	1,490	216,0	233,0	211,0	228,0
fi. 20,0	1,520	1,670	1,490	0,164	239,0	258,0	234,0	253,0
fi. 22,0	1,840	2,020	1,800	0,198	289,0	312,0	284,0	306,0
fi. 24,0	2,190	2,410	-	-	344,0	372,0	-	-
fi. 26,0	2,570	2,830	-	-	404,0	436,0	-	-